













## COMPOSITION

Syncron laminate 0,9 ± 0,1 mm thick.

## RECOMMENDED APPLICATIONS

Syncron Laminates offers matching laminates from the Syncron range, with the same finish for application in furniture and interior decoration.

### Physical and mechanical properties

Property	Result	Standard
 Stain resistance	Class 5	EN 14323
 Cold liquid resistance	Class 5	EN 14323
 Crack resistance	Class 5	EN 14323
 Light fastness	Blue: 8 Gray: 5	EN 14323
 Dry heat resistance	Class 5	EN 12722
 Damp heat resistance	Class 5	EN 12721
 Scratch resistance (diamond tip 0,09 mm)	3 ± 1 N	EN 14323
 Abrasion resistance	Class 1	EN 14323
 Steam resistance	Class 5	EN 14323
 Impact resistance	140 cm	EN 14323

---

## USE RECOMMENDATIONS

---

### Storage and cleaning




10°C  
40°C

Recommended storage temperature: 10°C - 40°C



30%  
70%

Recommended storage humidity: 30% - 70%



Do not expose to sunlight and others sources of heat for long time.



Clean with a soft cloth using water with mild soap.



Do not use any cleaners containing alcohol, solvents or abrasives.

---

### Notes

The applicable defect assessment conditions and quality standards are those defined in the Synchron board data sheet (see corresponding data sheet).

---