

COMPOSITION

Lacquered laminate 0.7 mm thick.

RECOMMENDED APPLICATIONS

Zenit Laminates offers matching laminates from the Zenit range, with the same finish for application in furniture and interior decoration.

Physical and mechanical properties

Property	Result	Standard
 Stain resistance	Class 5	EN 14323
 Cold liquid resistance	Class 5	EN 14323
 Cross cut adherence	Grade 1	ISO 2409
 Crack resistance	Class 5	EN 14323
 Light fastness	Blue: >6 Gray: 5	EN 14323
 Dry heat resistance	Class 5	EN 12722
 Damp heat resistance	Class 5	EN 12721
 Scratch resistance (diamond tip 0,09 mm)	3,5 ± 1 N	ISO 1518-1
 Abrasion resistance	Class 4	EN 14323
 Steam resistance	Class 5	EN 14323
 Impact resistance	200 cm	EN 14323
 Max. Colour difference between batches	$\Delta E \leq 0,70$	CIELab D65/10°
 Gloss (60°)	4 ± 1 GU	ISO 2813

 USE RECOMMENDATIONS

Storage and cleaning


10°C
40°C

Recommended storage temperature: 10°C - 40°C




30%
70%

Recommended storage humidity: 30% - 70%



The laminates must be consumed within 12 months of delivery to prevent the adhesive of the protective film from causing residue problems or excessive adhesion.



Do not expose to sunlight and others sources of heat for long time.



Clean with a soft cloth using water with mild soap.



Do not use any cleaners containing alcohol, solvents or abrasives.

Notes

The applicable defect assessment conditions and quality standards are those defined in the Zenit board data sheet (see corresponding data sheet).
